Report Number : TRPT24123224-REV1



Intertek India Private Limited
501, Opp. To LRG College, Palladam Road, Thennampalayam,Tirupur – 641604.
Tel : 91-421- 430 6600, Fax : 91-421-430 6700
Registered Office : E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site : www.intertek.com.

TEST REPORT

NUMBER : TRPT24123224-REV1
DATE : 02-Jan-2025

THIS IS TO SUPERSEDE REPORT NO. TRPT24123224 DATED 30-Dec-2024

Sample Description : ONE PIECE OF SUBMITTED WOVEN FABRIC SAMPLE

Applicant Provided Care Instructions :
MACHINE WASH AT 120+/-125°F, NORMAL CYCLE, TUMBLE DRY NORMAL

Date Received/Date Test Started : 21 Dec 2024

Color : WHITE
Style No : 16SX 8S/HALF PANAMA B
Fiber Content : 100% COTTON

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

AUTHORIZED BY
FOR Intertek India Private Limited [Tirupur]

SHANMUGAM KASI
LAB MANAGER

Intertek India Private Limited
501, Opp. To LRG College, Palladam Road, Thennampalayam,Tirupur – 641604.
Tel : 91-421- 430 6600, Fax : 91-421-430 6700
Registered Office : E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site : www.intertek.com.

TEST REPORT

NUMBER : TRPT24123224-REV1
DATE : 02-Jan-2025

CONCLUSION :

Dimensional Stability to Washing- 3 Wash Fab	*
Fabric Weight	*
Yarn Count	*
Fabric Construction	*
Colour Fastness to Washing	*
Colour Fastness to Rubbing	N/A
Tensile Strength	*
Tear Strength	*

NOTE : M = MEETS REQUIREMENT, F = FAILS TO MEET REQUIREMENT
* = REQUIREMENT NOT PROVIDED, N/A = NOT APPLICABLE
# = EXEMPTED NR = NOT REQUESTED
**=INCONCLUSIVE D = DATA
= SEE REMARK

1. Statement of conformity is based on the simple acceptance rule without using measurement uncertainty.
2. In this report results relate only to the item tested.
3. Laboratory reports the final test results in test report. Any additional information, if required will be provided on request.
4. Samples received in good condition.
5. Testing has been performed as per the applicant’s request.
6. Sampling is not done by Laboratory.
7. Environmental conditions followed at the time of testing as per International methods/customer requirements.

NOTE

Colour Fastness to Rubbing Test Was Not Applicable Since The Submitted Sample Is White Textiles.

The Report TRPT24123224 Is Superseded By TRPT24123224-REV1 To add Style Number As Per Applicant Request.

Intertek India Private Limited
501, Opp. To LRG College, Palladam Road, Thennampalayam,Tirupur – 641604.
Tel : 91-421- 430 6600, Fax : 91-421-430 6700
Registered Office : E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site : www.intertek.com.

TEST REPORT

NUMBER : TRPT24123224-REV1
DATE : 02-Jan-2025

Test Conducted (As Requested By The Applicant)

1. Dimensional Stability to Washing- 3 Wash Fab

AATCC 135:2018 [Test No (1) III A(ii), Machine Wash At 120°F, Normal Cycle Followed By Tumble Dry Low]

After 3Rd Wash

		Requirement
Warp [%]	[-] 7.0%	Not Provided
Weft [%]	[-] 2.7%	

2. Fabric Weight

ASTM D3776:2009 A(R):2013 /OPTION C

		Requirement
Gm./sq. Mtr	199.0	Not Provided
Oz./sq. Yds	5.9	

3. Yarn Count

ASTM D 1059: 2022

		Requirement
Warp	17.3 Ne	Not Provided
Weft	8.5 Ne	

REMARK:
[Ne] : Cotton Count

4. Fabric Construction

ASTM 3775-2023

Per Inch

		Requirement
Warp	88	Not Provided
Weft	28	

Intertek India Private Limited
501, Opp. To LRG College, Palladam Road, Thennampalayam,Tirupur – 641604.
Tel : 91-421- 430 6600, Fax : 91-421-430 6700
Registered Office : E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site : www.intertek.com.

TEST REPORT

NUMBER : TRPT24123224-REV1
DATE : 02-Jan-2025

5. Colour Fastness to Washing

AATCC 61 : 2013 E(2020) (2A Test,45 Mins Machine Wash At 120°F In 0.15% AATCC WOB Reference Detergent Solution With 50 Steel Balls)

		Requirement
Colour Change	4.5	Not Provided
COLOUR STAINING		
		Requirement
Acetate	5.0	Not Provided
Cotton	5.0	
Nylon	5.0	
Polyester	5.0	
Acrylic	5.0	
Wool	5.0	

6. Tensile Strength

ASTM D 5034:2021

		Requirement
Warp	93.8 lbf	Not Provided
Weft	52.0 lbf	

7. Tear Strength

ASTM D 2261:2017

		Requirement
Warp	8.9 lbf	Not Provided
Weft	6.1 lbf	

END OF THE TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Addressee in respect of this report and only accepts liability to the Addressee insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute.

http://www.intertek.com/terms.

Intertek India Private Limited
501, Opp. To LRG College, Palladam Road, Thennampalayam,Tirupur – 641604.
Tel : 91-421- 430 6600, Fax : 91-421-430 6700
Registered Office : E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site : www.intertek.com.